

Technical Data Sheet

EA

General Description

- Daylight and ultra-violet responsive fluorescent plastic colorants - free of formaldehyde - for plastics.
- A dyed/pigmented thermoplastic polyamide-ester resin.

Applications

- Recommended for extrusion, injection molding, blow molding, film blowing etc.

Product Features

- EA has a broad compatibility in many plastics with brilliant fluorescent colors and easy dispersion over a wide temperature range without formaldehyde out gassing.
- EA has the advantage of low mold plate-out, whereby both heat stability and light resistance are optimized.
- EA-3* series are recommended if extra color strength is desired.

Physical properties	
Delivery form	Powder
Particle size (Laser diffraction)	8.0 – 15.0 µm
Hegman grind	5.0 – 7.0
Melting point:	
EA-10/11/12/13/19/30/33	100 – 120°C
EA-14/15/16/17/18/35/37/38	120 – 140°C
Decomposition temp.	>300°C
Specific gravity	1.20 g/ml
Bulking value	0.3 – 0.4 g/ml

Test methods and Certificate of Analysis (COA) available on request.

Standard Colors

Product Name	Description
EA-10	Chartreuse
EA-11	Green
EA-12	Orange Yellow
EA-13	Orange
EA-14	Orange Red
EA-15	Red
EA-16	Cerise
EA-17	Pink
EA-18	Magenta
EA-19	Blue

High Strength Standard Colors

EA-30	Chartreuse
EA-33	Orange
EA-35	Red
EA-37	Pink
EA-38	Magenta

Packaging:

1 box = 20kg
MOQ = 20kg

Storage & shelf life:

120 months when kept in closed original packaging in a dry place at ambient temperature.

Safety & regulatory:

Safety Data Sheet available on request.

Processing

Heat stability	160°C – 240°C It is essential the minimum processing temperature of 160°C is reached in order to melt in the polymer and evenly distribute the pigment throughout the plastic. To minimize the influence of heat on the fluorescent properties, temperature impact needs to be hold as low as possible.
Plastics	Recommended for polyolefins (LDPE/HDPE/PP) and rubber. Other polymers should be tested.

EA pigments are designed for use at industrial sites as described in EU COMMISSION REGULATION 2023/2055 of 25 September 2023.

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.