

Technical Data Sheet

GMH

General Description

- A daylight fluorescent pigment based on a thermoset resin matrix for high temperature plastics processing to limit the loss of colour which may occur with other types of pigment.
- A dyed/pigmented thermoset copolymer.

Applications

- EVA foam, PVC plastisols and organosols, calendered PVC, extruded and injection moulded polyolefins, mass coloration of rubber.

Product Features

- Specifically designed for higher temperature plastics applications such as EVA foam.
- Minimal color change up to 30 minutes at 170°C.
- Small spherical particles ensures easy dispersion.
- Resistant to plate-out in plastics applications.
- Limited light-fastness in exterior exposure.

Standard Colors

Product Name	Description
GMH-20	Chartreuse
GMH-12	Orange Yellow
GMH-13	Orange
GMH-14	Orange Red
GMH-15	Red
GMH-17	Pink
GMH-8-1238	Magenta

Packaging:

1 box = 20kg
MOQ = 20kg

Storage & shelf life:

120 months when kept in closed original packaging in a dry place at ambient temperature.

Safety & regulatory:

Safety Data Sheet available on request.

Physical properties

Delivery form	Powder
Particle size (Laser diffraction)	± 3.0 µm
Hegman grind	5.0 - 7.0
pH of dye solution	4.5 – 7.0 (5% Aq. slurry)
Decomposition temp.	>250°C
Specific gravity	1.30 g/ml
Moisture Analysis	<4%

Test methods and Certificate of Analysis (COA) available on request.

Processing

Heat stability	>220°C
Solvent resistance	Resistant to and insoluble in most common solvents including ketones, esters and alcohols.

Pigments are insoluble and need to be dispersed (easily stir-in).

GMH pigments are designed for use at industrial sites as described in EU COMMISSION REGULATION 2023/2055 of 25 September 2023.

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.